

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan


“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 5454 (1978): Methods of sampling of clay building bricks
[CED 30: Clay and Stabilized Soil Products for
Construction]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



IS : 5454 -1918

REAFFIRMED
2010

Indian Standard
METHODS FOR SAMPLING OF
CLAY BUILDING BRICKS

(First Revision)

Fourth Reprint NOVEMBER 2005

UDC 691.421: 620 .113

© *Copyright* 1979

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Indian Standard

METHODS FOR SAMPLING OF CLAY BUILDING BRICKS

(*First Revision*)

Building Materials and Components Sampling
Sectional Committee, BDC 31

Chairman

SHRI G. D. JOGLEKAR
Telegaon (Dist Pune)

Members

Representing

SHRI J. S. BEDI	Doors, Windows and Shutters Sectional Committee, BDC 11, ISI
SHRI A. K. SOBTI (<i>Alternate</i>)	
SHRI B. B. BHATTACHARJEE	Concrete Reinforcement Sectional Committee, BSMDC 8, ISI
SHRI T. SEN (<i>Alternate</i>)	
SHRI J. D. DAROGA	Italab Engineering Pvt Ltd, Bombay
SHRI N. R. PATRAWALA (<i>Alternate</i>)	
SHRI K. H. GANDHI	Directorate General of Inspection (Ministry of Defence), New Delhi
SHRI SAT PAL SINGH (<i>Alternate</i>)	
SHRI S. K. GURNANI	Railway Board (Ministry of Railways)
SHRI M. S. EKBOTE (<i>Alternate</i>)	
SHRI P. J. JAGUS	Pozzolanas Sectional Committee, BDC 16, ISI
SHRI M. R. VINAYAKA (<i>Alternate</i>)	
SHRI K. P. JAIN	Builder's Hardware Sectional Committee, BDC 15, ISI
SHRI KARAMJIT SINGH	Central Public Works Department, New Delhi
SHRI K. K. KHANNA	Construction Plant and Machinery Sectional Com- mittee, BDC 28, ISI
SHRI A. C. MANNAN (<i>Alternate</i>)	
DR T. KRISHNAN	Indian Statistical Institute, Calcutta
SHRI S. R. KSHIRSAGAR	Sanitary Appliances and Water Fittings Sectional Committee, BDC 3, ISI
SHRI R. P. MISHRA (<i>Alternate</i>)	
SHRI N. C. MAJUMDAR	Clay Products for Building Sectional Committee, BDC 30, ISI

(*Continued on page 2*)

© Copyright 1979

BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS : 5454 - 1978

(Continued from page 1)

<i>Members</i>	<i>Representing</i>
SHRI M. R. MALYA	Bitumen and Tar Products Sectional Committee, ISDC 2, ISI
SHRI S. K. DUTTA (<i>Alternate</i>)	
COL Y. P. MISRA	Wood Products Sectional Committee, BDC 20, ISI
DR MOHAN RAI	Central Building Research Institute (CSIR), Roorkee
SHRI R. K. GOEL (<i>Alternate</i>)	
DR A. K. MULLICK	Cement Research Institute of India, New Delhi
DR M. PANCHOLY	Sieves Sectional Committee, BDC 19, ISI
SHRI S. S. RAJPUT	Forest Research Institute and Colleges, DehraDun
SHRI E. K. RAMACHANDRAN	National Test House, Calcutta
LALA G. C. DAS (<i>Alternate</i>)	
SHRI N. MOHAN RAO	Research & Development Organization (Ministry of Defence), New Delhi
SHRI V. B. GHORPADE (<i>Alternate</i>)	
SHRI A. C. SEKHAR	Timber Sectional Committee, BDC 9, ISI
SHRI C. A. TANEJA	Gypsum Building Materials Sectional Committee, BDC 21, ISI
DR B. N. SINGH, Director (Stat)	Director General, ISI (<i>Ex-officio Member</i>)

Secretary

SHRI N. C. TYAGI
Deputy Director (Stat), ISI

**AMENDMENT NO. 1 MARCH 2008
TO
IS 5454 : 1978 METHODS FOR SAMPLING OF CLAY
BUILDING BRICKS**

(First Revision)

(Page 7, clause 5.2.1.1, last line) — Substitute '15 percent' for '20 percent'.

(CED 30)

Reprography Unit, BIS, New Delhi, India

Indian Standard
METHODS FOR SAMPLING OF
CLAY BUILDING BRICKS
(*First Revision*)

0. FOREWORD

0.1 This Indian Standard (First Revision) was adopted by the Indian Standards Institution on 10 July 1978, after the draft finalized by the Building Materials and Components Sampling Sectional Committee had been approved by the Civil Engineering Division Council.

0.2 The clay building brick is the most extensively used building material in the construction work. Its quality is of fundamental importance in ensuring the soundness of the buildings and structures. It is, therefore, imperative that due consideration is given to the sampling procedures which would help in proper and objective evaluation of the quality of the bricks.

0.3 This standard was originally issued in 1969. However, in view of the experience gained in the course of years and the introduction of new and revised quality characteristics and methods of test in Indian Standards pertaining to various types of clay building bricks, it was felt necessary to revise this standard. In this revision, sampling procedures for breaking load, transverse strength and bulk density have been included. The criteria for conformity for efflorescence and compressive strength have been modified to bring them in line with the latest Indian Standards on specifications and methods of testing of clay building bricks.

0.4 In reporting the result of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS:2-1960*.

1. SCOPE

1.1 This standard lays down methods for sampling and criteria for ascertaining conformity of solid, hollow and perforated burnt clay building bricks to the relevant specifications.

*Rules for rounding off numerical values (revised).

2. TERMINOLOGY

2.0 For the purpose of this standard, the following definitions shall apply.

2.1 Lot — A collection of bricks of the same class and size, manufactured under relatively similar conditions of production. For the purpose of sampling, a lot shall contain a maximum of 50 000 bricks. In case a consignment has bricks more than 50 000 of the same classification and size, and manufactured under relatively similar conditions of production, it shall be divided into lots of 50 000 bricks or part thereof.

2.2 Sample — A collection of bricks selected for inspection and/or testing from a lot to reach the decision regarding the acceptance or rejection of the lot.

2.3 Defective — A brick failing to meet one or more of the specified requirements.

2.4 Average — The sum of the observations divided by the number of observations.

3. METHODS OF SAMPLING

3.1 The sample may be drawn either by: (a) random sampling, or (b) stratified sampling method in accordance with IS:4905-1968*.

3.2 The sample shall be taken by one of the methods given in 3.2.1, 3.2.2 or 3.2.3 so as to yield the number of bricks required.

3.2.1 Sampling in Motion — Whenever practicable the sample shall be taken while the bricks are being moved, for example, during loading or unloading. The lot shall be divided into a number of convenient portions (not less than ten). Approximately equal number of bricks shall be drawn from each of these portions at regular intervals, such that the requisite number of bricks for inspection and testing is provided.

3.2.2 Sampling from a Stack — When it is necessary to take a sample from a stack, the stack shall be divided into a number of real or imaginary sections and the required number of bricks drawn from each section. For this purpose bricks in the upper layers of the stack shall be removed to enable units to be sampled from places within the stack.

3.2.3 Sampling from Lorries or Trucks — When it is necessary to take a sample from bricks loaded in lorries or trucks, the sample bricks shall be taken from a number of lorries/trucks (not less than ten, if possible) such that when equal number of bricks are drawn from each of the lorries/trucks the number of bricks required for the inspection and testing is provided.

*Methods for random sampling.

4. SCALE OF SAMPLING AND CRITERIA FOR CONFORMITY FOR VISUAL AND DIMENSIONAL CHARACTERISTICS

4.1 The bricks shall be selected and inspected for each lot separately for ascertaining their conformity to the requirements of the relevant specification.

4.1.1 The number of bricks to be selected from a lot shall depend on the size of the lot and shall be in accordance with col 1 and 2 of Table 1 for visual characteristics in all cases and dimensional characteristics if specified for individual brick. In case dimensions are specified for a group of 20 bricks, the scale of sampling for dimensional characteristics shall be in accordance with col 1 and 4 of Table 1. All these bricks shall be selected following the methods detailed in 3.

4.2 Visual Characteristics—All the bricks selected as in 4.1.1 in accordance with col 1 and 2 of Table 1 shall be examined for visual characteristics. If the number of defective bricks found in the sample is less than or equal to the corresponding number as specified in col 3 of Table 1, the lot shall be considered as satisfying the requirements of the visual characteristics. However, if the number of defective bricks in the sample is greater than the corresponding permissible number of defectives, the lot shall be deemed as not having met the visual requirements.

TABLE 1 SCALE OF SAMPLING AND PERMISSIBLE NUMBER OF DEFECTIVES FOR VISUAL AND DIMENSIONAL CHARACTERISTICS

(Clauses 4.1.1, 4.2 and 4.3.2)

No. of BRICKS IN THE LOT	FOR CHARACTERISTICS SPECIFIED FOR INDIVIDUAL BRICK		FOR DIMENSIONAL CHAR- ACTERISTICS SPECIFIED FOR GROUP OF 20 BRICKS—No. OF BRICKS TO BE SELECTED
	No. of Bricks to be Selected	Permissible No. of Defectives in the Sample	
(1)	(2)	(3)	(4)
2 001 to 10 000	20	1	40
10 001 to 35 000	32	2	60
35 001 to 50 000	50	3	80

NOTE — In case the lot contains 2 000 or less bricks, the sampling shall be subject to agreement between the purchaser and the supplier.

4.3 Dimensional Characteristics— The dimensions and tolerances have been specified in various standards for clay building bricks. In some standards the dimensions and tolerances have been specified for individual brick. In some other standards the dimensions and tolerances have been specified for a group of 20 bricks.

4.3.1 In case the dimensions and tolerances have been specified for individual brick, the scale of sampling and criteria for conformity shall be the same as laid down in 4.2 for visual characteristics.

4.3.2 In case the dimensions and tolerances for bricks are specified as overall on a group of 20 bricks, the number of bricks to be selected for inspecting the dimensions and tolerances shall be in accordance with col 1 and 4 of Table 1. These bricks will be divided into groups of 20 bricks at random and each of the groups thus formed tested for all the dimensions and tolerances. A lot shall be considered having found meeting the requirements of dimensions and tolerances if none of the groups of bricks inspected fails to meet the specified requirements.

5. SCALE OF SAMPLING AND CRITERIA FOR CONFORMITY FOR PHYSICAL CHARACTERISTICS

5.1 The lot which has been found satisfactory in respect of visual and dimensional requirements (*see* 4.2 and 4.3) shall next be tested for physical characteristics like compressive strength, breaking load, transverse strength, bulk density, water absorption, efflorescence and warpage as specified in relevant material specification. The bricks for this purpose shall be taken at random from those already selected in 4.1.1. The number of bricks to be selected and tested for each of these characteristics shall be in accordance with relevant columns of Table 2.

TABLE 2 SCALE OF SAMPLING FOR PHYSICAL CHARACTERISTICS

(Clauses 5.1, 5.2.3 and 5.2.4)

LOT SIZE	SAMPLE SIZE FOR COMPRES- SIVE STRENGTH, BREAKING LOAD, TRANSVERSE STR- ENGTH, BULK DENSITY, WATER ABSORPTION AND EFFLORESCENCE	PERMISSIBLE NO. OF DEFECTIVES FOR EFFLOR- ESCENCE	WARPAGE	
			Sample Size	Permissible No. of Defectives
(1)	(2)	(3)	(4)	(5)
2 001 to 10 000	5	0	10	0
10 001 to 35 000	10	0	20	1
35 001 to 50 000	15	1	30	2

NOTE — In case the lot contains 2 000 or less bricks, the sampling shall be subject to agreement between the purchaser and the supplier.

5.2 A lot shall be considered having satisfied the requirements of physical characteristics if the conditions stipulated in 5.2.1, 5.2.2, 5.2.3 and 5.2.4 are all satisfied.

5.2.1 From the test results for compressive strength, breaking load, and transverse strength (whichever applicable), the average shall be calculated and shall satisfy the requirements specified in the relevant material specification.

NOTE — In case any of the test results for compressive strength exceeds the upper limit for the class of brick, the same shall be limited to the upper limit of the class for the purpose of averaging.

5.2.1.1 Wherever specified in the material specification the compressive strength of any individual brick tested in the sample shall not fall below the minimum average compressive strength specified for the corresponding class of brick by more than 20 percent.

5.2.2 From the test results for water absorption and bulk density the average for the bricks in the sample shall be calculated and shall satisfy the relevant requirements specified in the material specification.

5.2.3 The number of bricks failing to satisfy the requirements of the efflorescence specified in the relevant specification shall not be more than the permissible number of defectives given in col 3 of Table 2.

5.2.4 The number of bricks failing to satisfy the requirements of warpage wherever specified in the relevant specifications shall not be more than the permissible number of defectives given in col 5 of Table 2.

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 23230131, 23233375, 23239402

Fax: 91+011 23234062, 23239399, 23239382

E-mail: bis@vsnl.com

website: <http://www.bis.org.in>

Central Laboratory:

Plot No. 20/9, Site IV, Sahibabad Industrial Area, SAHIBABD 201010

Telephone

2770032

Regional Offices:

Central: Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

23237617

*Eastern: 1/14 CIT Scheme VII M, V.I.P. Road Kankurgachi, KOLKATA 700054

23378662

Northern: SCO 335-336, Sector 34-A, Chandigarh 160022

603843

Southern: C.I.T. Campus, IV Cross Road, CHENNAI 600113

254 19 84

Western: Manakalaya, E9, MIDC, Behind Marol Telephone Exchange,

2832 92 95

Andheri (East), MUMBAI 400093

Branch offices:

'Pushpak' Nurmohamed Shaikh Marg, Khanpur, AHMEDABAD 380001

560 13 48

Peenya Industrial Area, 1st Stage, Bangalore-Tumkur Road, BANGALORE

839 49 55

Commercial-cum-office Complex, opp. Dushera Maidan, Arera Colony,

242 34 52

Bittan Market, BHOPAL 462016

62/63, Ganga Nagar, Unit VI, BHUBANESHWAR 751001

240 3139

5th Floor, Koval Towers, 44 Bala Sundaram Road, COIMBATORE 641018

221 0141

SCO 21, Sector 12, Faridabad 121007

2292175

Savitri Complex, 116 G.T. Road Ghaziabad 201001

2861498

53/5 Ward No. 29, R.G. Barua Road 5 by-lane, Apurba Sinha Path

2541137

GUWAHATI 781003

5-8-56C L.N. Gupta Marg, Nampally Station Road, HYBERABAD 500001

23201084

E-52, Chitrangan Marg, C-Scheme, JAIPUR 302001

2373879

117/418 B Sarvodaya Nagar, KANPUR 208005

2218774

Sethi Bhavan: 2nd Floor, Behind Leela Cinema, Naval Kishore Road,

2215698

LUCKNOW 226001

NIT Building, Second Floor, Gokulpat Market, NAGPUR 440010

2525171

Mahavir Bhavan, First Floor, Ropar Road, NALAGARH 174101

221451

Patliputra Industrial Estate, PATNA 800013

2262808

First Floor, Plot Nos 657-660, Market Yard, Gultkdi, PUNE 411037

4268659

Sahajanand House 3rd Floor, Bhaktinagar Circle, 80 Feet Road,

2378251

RAJKOT 380002

T.C. No. 14/1421, University P.O. Palayam, THIRUVANANTHAPURAM 695034

2322104

1st Floor, Udyog Bhavan, VUDA, Siripuram Junction, VISHAKHAPATNAM-03

2712833

Sales Office is at 5 Chowringhee Approach, P.O. Princep Street, Kolkata 700072

22371085

Sales Office is at Novelty Chambers, Grant Road, MUMBAI 400007

23096528